

Hydrogel-Based Nanostructured 3D Scaffolds for Bone Tissue Regeneration: Properties and Tools

Brasinika D, Dragatogiannis D and Charitidis CA*

Research Unit of Advanced, Composite, Nano-Materials and Nanotechnology, School of Chemical Engineering, National Technical University of Athens, Greece

*Corresponding author: Charitidis CA, Research Unit of Advanced, Composite, Nano-Materials and Nanotechnology, School of Chemical Engineering, National Technical University of Athens, Greece, E-mail: charitidis@chemeng.ntua.gr

Tissue engineering necessitates the development of optimized scaffolds that facilitate cell growth and tissue development and regeneration. Bone regeneration is a complex biological process, including the recruitment of osteoprogenitor cells in the injured tissue and the utilization of a porous scaffold along with growth factors to induce tissue formation.

An ideal scaffold should address multiple physicochemical and biological requirements (e.g. biocompatibility, osteoconductivity, osteoinductivity) and serve as a 3D porous matrix, with interconnected open porosity, for cellular growth, proliferation, differentiation and subsequent extra-cellular matrix (ECM) development.

Moreover, stable material-tissue interface together with adequate mechanical strength and controlled degradation rate must be achieved so as to provide structural integrity, until the desired tissue is regenerated naturally [1]. Recently, nanoindentation techniques have gained significant attention in the area of soft biological tissues and are being rapidly adopted to investigate mechanical properties of scaffolds, mimicking soft tissues, and elucidate the effect of degradation process in a wet environment. Accuracy of measurements especially in wet conditions requires new methods and techniques since hydrogels possess time dependent poro-elastic or poro-viscoelastic behavior and liquid capillarity and proper surface detection add major challenges [2,3].

Nanostructured hydrogel-based scaffolds have been studied intensively in the field of tissue engineering, since they provide a highly water-swollen polymeric network, resembling structure complexity of natural connective soft tissues. Their 3D structure consists mainly of chemically or physically cross-linked hydrophilic polymers (natural or synthetic), whose ability to swell in aqueous medium lead to the entrapment of cells inside the scaffold and to high permeability of oxygen, nutrients and cellular metabolites [4].

Porosity of bone substitutes is prerequisite, in order to allow high density of seeded cells and to support neovascularization when being implanted in vivo. In addition, porous structure increases mechanical interlocking between the implanted scaffold and the surrounding natural tissue, providing enhanced mechanical stability at the critical interface [5]. The relationship between pore size and osteoblastic activity is not fully determined; however a porous network consisting of both macropores (pore size $\geq 50 \mu\text{m}$) and micropores (pore size $\leq 10 \mu\text{m}$) has been proved beneficial for new tissue in growth [6]. Furthermore, by varying pore parameters, the biodegradation rate of the scaffolds is affected, since higher porosity increases surface area per unit volume.

Hydrogel-based scaffolds with an inner porous network are currently being fabricated by a variety of methods, such as gas foaming, solvent

Received date: 18 Dec 2015; Accepted date: 21 Dec 2015; Published date: 27 Dec 2015.

Citation: Brasinika D, Dragatogiannis D, Charitidis CA (2015) Hydrogel-Based Nanostructured 3D Scaffolds for Bone Tissue Regeneration: Properties and Tools. *Int Nanomed Nanosurg* 2(1): doi <http://dx.doi.org/10.16966/2470-3206.e103>

Copyright: © 2015 Brasinika D, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

casting and particulate leaching, thermally induced phase separation or freeze drying [7]. The drawbacks of these techniques arise mainly from the utilization of highly toxic organic solvents, the incomplete removal of residues from the polymeric structures and the lack of full control over the interconnectivity of the pores. Additionally, most of these methods fail in producing scaffolds with tailored pore size and shape. To overcome these restrictions, additive manufacturing approaches can be employed to design and fabricate 3D scaffolds with a specific complex architecture. One of the most promising technologies includes 3D printing and more specifically Direct Ink Writing of hydrogel scaffolds [8]. During this process a virtual 3D model of the scaffold is created from a computer tomography data set and, subsequently, the material is extruded from a syringe nozzle in a layer-by-layer way, enabling formation of a well-defined porous structure with precise controlled interconnectivity. Moreover, in bone tissue engineering, 3D printing appears as a versatile tool for the direct fabrication of personalized implants, by exploiting computer aided design (CAD) programs.

References

1. Lima PAL, Resende CX, Soares GD de Almeida, Anselme K, Almeida LE (2013) Preparation, characterization and biological test of 3D-scaffolds based on chitosan, fibroin and hydroxyapatite for bone tissue engineering. *Mater Sci Eng C* 33: 3389-3395.
2. Pharr GM (2015) Recent advances in small-scale mechanical property measurement by nanoindentation. *Curr Opin Solid State Mater Sci* 19: 315-316.
3. Skarmoutsou A, Lolas G, Charitidis CA, Chatzinikolaidou M, Vamvakaki M, et al. (2013) Nanomechanical properties of hybrid coatings for bone tissue engineering. *J Mech Behav Biomed Mater* 25: 48-62.
4. Billiet T, Vandenhaute M, Schelfhout J, Vlierberghe SV, Dubrue P (2012) A review of trends and limitations in hydrogel-rapid prototyping for tissue engineering. *Biomaterials* 33: 6020-6041.
5. Bose S, Roy M, Bandyopadhyay A (2012) Recent advances in bone tissue engineering scaffolds. *Trends in Biotechnology* 30: 546-554.
6. Liu Y, Li X, Qu X, Zhu L, He J, et al. (2012) The fabrication and cell culture of three-dimensional rolled scaffolds with complex micro-architectures. *Biofabrication* 4: 015004.
7. Lu T, Li Y, Chen T (2013) Techniques for fabrication and construction of three-dimensional scaffolds for tissue engineering. *Int J Nanomed* 8: 337-350.
8. Bose S, Vahabzadeh S, Bandyopadhyay A (2013) Bone tissue engineering using 3D printing. *Mater Today* 16: 496-504.